



CEWELD Ni-Rod 44

TYPE Solid Nickel-Iron-Manganese welding wire for cast iron

ANWENDUNGEN Ductile, gray and malleable Cast Iron and cast steel repairs, rebuilding wornout parts and also suitable for joining steel to cast Iron.

EIGENSCHAFTEN Excellent wetting properties that enable this welding wire to weld with high welding speed due to the high manganese content. Thermal expansion is very low (close to NILO) and the weld deposit is extreme crack resistant.

KLASSIFIKATION AWS A 5.15: E NiFeMn-CI
EN ISO 1071: NiFeMn-CI

GEEIGNET FÜR Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.

ZULASSUNGEN

SCHWEISSPOSITIONEN



**TYPISCHE CHEMISCHE
ANALYSE DES
SCHWEISSMETALLS (%)**

C	Si	Mn	Ni	Al	Fe
0.25	0.08	12	42	0.3	Rem.

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		690	35	190 HB

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1