



CEWELD AA B57-62

TYPE Seamless medium alloyed basic fluxcored wire with slag for hardfacing using Ar-CO2 mix

ANWENDUNGEN Rebuilding and cladding parts against strong abrasion and heavy impact.

EIGENSCHAFTEN Due to the high resistance to cracking and toughness, all weld metal requires no buffer layer except on materials considered critical. In this situation CEWELD® ER 100 S-G is recommended. Suited for wear parts subject to heavy impact and shock. The interpass temperature should be maximum 250°C. The weld metal is machinable by special carbide tools, hardening is possible. The maximum hardness is dependent on the base metal and is achieved in the first layer. For material considered critical to cracking we advise to buffer with one layer CEWELD® AA B460.

KLASSIFIKATION EN ISO 14700: T Fe4

GEEIGNET FÜR 55-62 HRc hardfacing alloy against heavy impact and shock, bucket, loaders, crusher jaws, crusher cones, pumps, sand, snow scratchers, stone cutting tools etc.

ZULASSUNGEN

SCHWEISSPOSITIONEN



**TYPISCHE CHEMISCHE
ANALYSE DES
SCHWEISSMETALLS (%)**

C	Si	Mn	Cr	Mo
0.5	0.6	1.5	6	0.5

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded				60 HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 M21