


CEWELD L-CuP7

TYPE	Copper Phosphorus Brazing Alloy.				
APPLICATIONS	Joining: Copper to copper, Copper alloys, Brass, Copper-Sn alloys with flux. Do not use this alloy above working temperatures of 200 °C				
PROPERTIES	Universal brazing alloy containing phosphor for use without additional flux on copper to copper joints. Good flowing characteristics very easy to use with high mechanical properties.				
CLASSIFICATION	AWS EN ISO F-nr	A 5.8: BCuP-2 17672: CuP 181 103			
SUITABLE FOR	Copper to Copper (without flux), Copper alloys, Brass, Copper-Sn alloys with flux.				
APPROVALS					
WELDING POSITIONS					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Cu Rem.		P 7.2		
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded		250		HRc
REDRYING	Not required				
MELTING RANGE	710 - 793°C				
GAS ACC. EN ISO 14175					



CEWELD L-CuP7

L-CUP7 1,5MM

Packaging	KG/unit	EanCode
D-300	10	8720663421241