



CEWELD Cu 58

TYPE	Pure copper wire for welding applications													
APPLICATIONS	continious resistance welding of steel plates, metal cans etc.													
PROPRIÉTÉS	• High quality 99.9% pure copper wire • Excelent electrical conductivity • Excellent corrosion resistance													
CLASSIFICATION														
CONVIENT POUR	Sudronic welding of steel cans and sheet metal in general metal fabrication. Usually the wire is in the F21 condition.													
AGRÉMENTS														
POSITIONS DE SOUDAGE	     													
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	<table><tr><td>Cu</td><td>Pb</td><td>O</td></tr><tr><td>99.9</td><td>0.005</td><td>0.04</td></tr></table>	Cu	Pb	O	99.9	0.005	0.04							
Cu	Pb	O												
99.9	0.005	0.04												
PROPRIÉTÉS MÉCANIQUES	<table><tr><th rowspan="2">Heat Treatment</th><th rowspan="2">R_{P0,2} (MPa)</th><th rowspan="2">R_m (MPa)</th><th rowspan="2">A5 (%)</th><th>Impact Energy (J) ISO-V</th><th rowspan="2">Hardness</th></tr><tr><th>RT</th></tr><tr><td>As Welded</td><td>200</td><td>300</td><td>40</td><td>60</td><td>HRc</td></tr></table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Impact Energy (J) ISO-V	Hardness	RT	As Welded	200	300	40	60	HRc
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)		A5 (%)	Impact Energy (J) ISO-V	Hardness				
		RT												
As Welded	200	300	40	60	HRc									
ETUVAGE	Not required													
GAS ACC. EN ISO 14175	I1, I3													



CEWELD Cu 58

CU 58 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663408174

CU 58 2,0MM

Packaging	KG/unit	EanCode
Drum	250	8720663408167