



CEWELD S2 CrMo2

TYPE	Submerged Arc wire for welding temperature resistant boiler steels and base metals.						
TOEPASSINGEN	Typical applications in power generation plant include steam piping, turbines and boilers; the alloy also finds applications in the chemical and petrol-chemical industries.						
EIGENSCHAPPEN	Submerged arc welding wire for high temperature creep resistant 2,45%Cr 1,0%Mo ferritic steel. These steels are used for creep resisting applications up to ~550°C. The wire has low levels of tramp elements (e.g. Sn, As, Sb and P) providing a low Bruscato Factor (X< 10 ppm) for temper embrittlement resistant applications. Recommended flux: FL 155						
CLASSIFICATIE	AWS	A 5.23: EB3					
	EN ISO	24598-A: S CrMo2					
	F-nr	6					
	FM	3					
GESCHIKT VOOR	2,25% Cr, 1% Mo 1.7015, 1.7131, 1.7147, 1.7380, 1.7337, 1.7262, 1.7258, 1.7350, 1.7357, 1.7375, 1.7379, 1.7383, 1.7385, 1.7707, 1.8075 10CrMo9.10, 12CrMo9-10, 10CrSiMoV7, 12CrSiMo8, 30CrMoV9, GS-18CrMo9.10, 15CrMoV5-10, 16CrMo4-4, 15CrMo5, 24CrMo5, 22CrMo4-4, GS-17CrMo5-5, 15Cr3, 16MnCr5, 20MnCr5, 10CrSiV7, ASTM: A 387 Gr. 22, A217 Grade WC9, A335 Gr. P22, A217 Gr. WC9, A182 F22, A182 T22, A1031 Gr.5015, A1031 Gr.5115, A1031 Gr.4820						
GOEDKEURINGEN	CE						
LASPOSITIES	 PA  PB  PC						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Mo
	0.1	0.25	0.6	0.01	0.01	2.45	1
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
	690°C±15°C 3h	490	600	24	RT	-20°C	HRc
HERDROGEN	Not required						
GAS ACC. EN ISO 14175							



CEWELD S2 CrMo2

S2 CRM02 3,2MM

Packaging	KG/unit	EanCode
K-415	25	8720663404800

S2 CRM02 4,0MM

Packaging	KG/unit	EanCode
K-415	25	8720663424303