



CEWELD CuAl8Ni2

TYPE	Mig Aluminium / Nickel alloyed copper welding wire							
TOEPASSINGEN	Joint welds or building up of aluminum bronze. Cladding components undergoing metal to metal wear under high pressure. Especially suited for marine environments. The addition of nickel improves corrosion resistance in heat and rough seawater.							
EIGENSCHAPPEN	CEWELD® CuAl8Ni2 is a special alloyed copper wire for the MIG process. The weld metal is a Cu-Al-Ni bronze. Sound, pore free deposits on ferrous and non-ferrous base materials. Excellent resistance to cavitations and stress corrosion cracking.							
CLASSIFICATIE	EN ISO	24373: Cu 6327 / CuAl8Ni2Fe2Mn2						
	W.Nr.	2.0922						
	F-nr	36						
GESCHIKT VOOR	This filler metal with increased strenght and corrosion properties is verry wel suited for Ship propellers, shipbuilding, pump building, shafts, guide grooves etc. W.Nrs: 2.0916,2.0920, 2.0928, 2.0932, 2.0936, 2.0940, 2.0960, 2.0962, 2.0966, 2.0970, 2.0978, 2.0980.							
GOEDKEURINGEN								
LASPOSITIES	 PA  PB  PC  PD  PE  PF  PG							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Mn	Fe	Cu	Zn	Pb	Al	Ni+Co
	0.1	2	2	Rem.	0.1	0.01	8.5	2
MECHANISCHE WAARDEN	Heat Treatment		RP0,2 (MPa)	Rm (MPa)	A5 (%)	Hardness		
	As Welded			580		140 HB		
HERDROGEN	Not required							
GAS ACC. EN ISO 14175	I1, I3							



CEWELD CuAl8Ni2

CUAL8NI2 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663409164

CUAL8NI2 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663409171

CUAL8NI2 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663409270
BS-300	15	8720663409300