CEWELD G4

certilas® THE FILLER METAL SPECIALIST

TYPE

High strength Mn / Mo- alloyed filler metal for flame and Tig welding with extreme good flowing properties without spatters during welding.

TOEPASSINGEN

Finegrain and creep resistant molybdenum containing steels. Suitable for working temperatures up to 500°Celsius. It's suited in trade and industry for welding plates, pipes, boilers and other profiles.

EIGENSCHAPPEN

High strength Manganese-Molybdenum- alloyed filler metal for flame welding with extreme good flowing properties without spatters during welding. Excelent mechanical strenght due to the addition of Molybdenium.The deposit is homogenous and suitable for heat treatment (PWHT).

CLASSIFICATIE

AWS	A 5.2: R60-G
EN ISO	20378: O IV
F-nr	6
FM	1

GESCHIKT VOOR

Typ 0,5Mo ≤ 460 MPa, ISO 15608: 1.2, 1.3
1.5415, 1.0481, 1.0482
15Mo3, 16Mo3, 20MnMoNi4-5, 15NiCuMoNb5, S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE300
ASTM: A 29 Gr. 1013, 1016; A 106 Gr. C; A, B; A 182 Gr. F1; A 234 Gr. WP1; A 283 Gr. B, C, D; A 335 Gr. P1; A 501 Gr. B; A 533 Gr. B, C; A 510 Gr. 1013; A 512 Gr. 1021, 1026; A 513 Gr. 1021, 1026; A 516 Gr. 70; A 633 Gr. C; A 678 Gr. B; A 709 Gr. 36, 50; A 711 Gr. 1013;
API 5 L B, X42, X52, X60, X65

GOEDKEURINGEN

CE

LASPOSITIES

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	Mo
0.12	0.2	1.1	0.5

MECHANISCHE WAARDEN

Heat Treatment	$R_{P0,2}$ (MPa)	Rm (MPa)	A5 (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	350	500	22	60	HRc

HERDROGEN

Not required

GAS ACC. EN ISO 14175

None